

TECHNICAL DATA SHEET

Product code & description:

URC1002 WESTACURE RC HIGH GLOSS COATING

Application:

URC1002 WESTACURE RC HIGH GLOSS COATING is a UV curable overprint varnish designed for roller /anilox coater application. Product has high gloss with high slip, good flow and leveling characteristics on paper / board, coated Metpet.

Key Properties:

- Excellent Gloss
- High Slip
- Good Flow & Levelling
- High abrasion resistance
- Water Repellent
- Good chemical resistance
- Good adhesion (on coated flexible substrates)

Substrate:

Suitable for low absorbent paper and board & yield better result if a water-based primer coat is applied.
Suitable for use on coated Metallized Polyester (≥ 42 dynes/cm) - preferably primer coated by either solvent or water-based varnish.

Instructions for Use

- | | |
|------------------------|---------------------------------|
| ● Stir well before use | |
| ● Application | Roller coater /Anilox coater |
| ● Viscosity | Ready for use |
| ● Varnish coat weight | 3 — 4 gsm (as per requirement) |
| ● Cleaning | Immediately with proper solvent |

Curing:

The RC Ink converts into a solid film by radical polymerization initiated by UV radiation in the range of 200 -400 nm. Capacity of the lamp is 80 -120 watts/cm.

Machine Speed

Depends on the type and age of the lamp

Technical Characteristics:

Color Appearance:	Clear liquid
Viscosity by Ford Cup#B4@30°C:	40 ± 2 Sec
Density:	1.07 – 1.10
Volatility:	0 %

Product safety:

UV products are generally considered to be non-toxicological. However, during handling and use, avoid inhalation of vapor and direct eyes or skin contact. It can be irritating, wash and rinse immediately with soap & water. Protective eyewear and latex gloves are recommended while using this product. Refer MSDS for additional handling and safety information.

Shelf life:

URC1002 is stable for 6 months when stored in its original container at temperatures between 5°C and 25°C, away from direct sunlight. Contaminated material should not be returned to the original container or re-used.

Cleaning:

Clean the rubber roller, steel roller, anilox roll and other equipment with recommended cleaning agent, after use.

Packaging:

This product is available in 20Kg plastic carboy.

NOT SUITABLE FOR DIRECT CONTACT FOOD PACKAGING

Disclaimer:

This information is furnished without warranty, expressed, or implied, except that it is accurate to the best knowledge of Westtek Enterprises Private Limited. The data on the sheet is related to specific product designated herein. Westtek Enterprises Private Limited assumes no legal responsibility for use or reliance upon these data.

Issued Date: Feb 2023 - Version: V1.1
