

TECHNICAL DATA SHEET

Product code & description:

URC1003 WESTACURE RC INK – LOW ODOUR

Application:

URC1003 WESTACURE RC INK is a low odour UV curable overprint varnish designed for roller /anilox coater application which produces excellent gloss on coated paper & board.

Key Properties:

- Free from Benzophenone (CAS No.119-61-9), 4 methyl benzophenone (CAS No. 134-84-9) & ITX (CAS No. 5495-84-1)
- High Gloss
- High Scuff
- Very Good surface slip
- High abrasion resistance
- > Water Repellent
- Good chemical resistance

Substrate:

Suitable for low absorbent paper and board & yield better result if a water-based primer coat is applied.

Instructions for Use:

.

- Stir well before use
 - Roller coater /Anilox coater
- Viscosity
- Ready for use
- VISCOSILY

Application

- veight 3 4 gsm (as per requirement)
- Varnish coat weight 3 4 gsm (as p
- Cleaning
 Immediately with proper solvent

Curing:

The RC Ink converts into a solid film by radical polymerization initiated by UV radiation in the range of 200 -400 nm. Capacity of the lamp is 80 -120 watts/cm.

Machine Speed:

Depends on the Type and age of the lamp.

Technical Characteristics:	
Color Appearance:	Clear transparent liquid
Viscosity by Ford Cup#B4@30°C:	46± 2 Sec
Density:	1.07 - 1.10
Volatility:	0 %

Product safety:

UV products are generally considered to be non-toxicological. However, during handling and use, avoid inhalation of vapor and direct eyes or skin contact. It can be irritating, wash and rinse immediately with soap & water. Protective eyewear and latex gloves are recommended while using this product. Refer MSDS for additional handling and safety information.

Shelf life:

URC 1003 is stable for 6 months when stored in its original container at temperatures between 5°C and 25°C, away from direct sunlight. Contaminated material should not be returned to the original container or re-used.

Cleaning:

Clean the rubber roller, steel roller, anilox roll and other equipment with recommended cleaning agent, after use.

Packaging:

This product is available in 20Kg plastic carboy.

NOT SUITABLE FOR DIRECT CONTACT FOOD PACKAGING

Disclaimer:

This information is furnished without warranty, expressed, or implied, except that it is accurate to the best knowledge of Westtek Enterprises Private Limited. The data on the sheet is related to specific product designated herein. Westtek Enterprises Private Limited assumes no legal responsibility for use or reliance upon these data.

Issued Date: Feb 2023 - Version: V1.1

Westtek Enterprises Private Limited-Public Document

Page 1 of 1